

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 027 381 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
20.03.2002 Bulletin 2002/12

(51) Int Cl.7: **C08G 18/08, C08G 18/12**

(86) International application number:
PCT/US98/22970

(21) Application number: **98956329.1**

(87) International publication number:
WO 99/23129 (14.05.1999 Gazette 1999/19)

(22) Date of filing: **29.10.1998**

(54) **WATERBORNE POLYURETHANE HAVING FILM PROPERTIES COMPARABLE TO RUBBER**

**WÄSSRIGE POLYURETHANE UND DARAUS HERGESTELLTE FILME MIT ELASTISCHEN
EIGENSCHAFTEN**

**POLYURETHANNE EN PHASE AQUEUSE AYANT DES CARACTERISTIQUES DE FILM
COMPARABLES A CELLES DU CAOUTCHOUC**

(84) Designated Contracting States:
**AT BE CH DE DK ES FI FR GB GR IE IT LI LU NL
PT SE**

(30) Priority: **31.10.1997 US 962435**

(43) Date of publication of application:
16.08.2000 Bulletin 2000/33

(73) Proprietor: **Noveon IP Holdings Corp.**
Cleveland, OH 44141-3247 (US)

(72) Inventors:
• **SNOW, George, E.**
Medina, OH 44256 (US)

• **DAME, Tina, R.**
Brunswick, OH 44212 (US)

(74) Representative:
Weber, Thomas, Dr.Dipl.-Chem. et al
Patentanwälte
von Kreisler-Selting-Werner,
Postfach 10 22 41
50462 Köln (DE)

(56) References cited:
EP-A- 0 148 970 **EP-A- 0 426 883**
EP-A- 0 741 152 **US-A- 5 086 110**
US-A- 5 354 807

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 027 381 B1

Description**Background of the Invention****1. Field of the Invention**

[0001] This invention relates to a waterborne polyurethane. More particularly, the invention relates to a waterborne polyurethane useful as a film, the film having improved properties comparable to or even exceeding those of rubber, i.e., a percentage elongation greater than 700%, a tensile strength greater than 3500 psi, a 100% modulus below 450 psi, a 300% modulus below 700 psi, and a 500% modulus below 1500 psi.

2. Description of the Prior Art

[0002] Many medical devices, particularly protective products, devices and films such as gloves for medical and industrial applications, contraceptive devices, catheters, balloons, cuffs, wound care, and various tubing are manufactured from materials having elastomeric properties. By "elastomeric properties" it is meant that the substance can be stretched at room temperature to at least twice its original length, and, after having been stretched and the stress removed, returns with force to approximately its original length within a short time.

[0003] A material having elastomeric properties is also known as an elastomer — the generic term for a rubber. A rubber is defined as a natural, synthetic, or modified high polymer with elastic properties, and, after vulcanization, elastic recovery. The terminology "rubber" is meant to include both natural rubber and synthetic rubber — denoted *cis*-1,4-polyisoprene, which has extensively been used in the past in the manufacture of many goods, including the aforementioned protective products, devices, and films. Typically, the rubber is initially available as a rubber latex, i.e., a colloidal suspension of the rubber in an aqueous medium, which is then used in the production of the rubbery material.

[0004] Use of a rubber latex to manufacture these articles can be problematic from several different perspectives. Because rubber latex is a natural product, it is subject to inherent variations and inconsistencies, which require compensation during the manufacturing process in order to maintain adherence to process and performance requirements. The rubber latex is also susceptible to bacterial degradation, which requires the manufacturer to periodically clean out the process and scrap such material.

[0005] Further, the number of latex allergy incidents has been growing rapidly since 1989. In that year, the FDA received its first reports of patients, who when exposed to natural latex medical devices, died from anaphylactic shock. An estimated 15% of the healthcare worker population and a small percentage of the overall population are now sensitive to natural latex. The immunoglobulin E (IgE) latex allergy can manifest itself in three types of reactions;

Type IV: Delayed hypersensitivity (allergic contact dermatitis)
 Type II: Irritation (non-allergic)
 Type I: Immediate Hypersensitivity (allergic)

[0006] The most common allergic response is type IV, a type of contact dermatitis caused by not only the protein in natural rubber latex, but by the additives which improve its properties. These additives include sulfur and sulfur based chemicals and accelerators, mercaptobenzothiazoles, thiurams, carbamates, and phenylene diamines. The type I is the most serious, and possibly fatal, allergic response.

[0007] Because of these past problems associated with the manufacture and use of rubber, polyurethane materials have been substituted for rubber in some applications. Polyurethanes are advantageous because they can be biocompatible, can be formed into films with high water vapor transmission, are cooler to wear, and are oil resistant and do not swell in the presence of body oils.

[0008] Use of these prior art polyurethane materials, though, has been problematic for several reasons. For example, many of these materials must be extruded, thermoformed or solubilized in an organic solvent to be shaped for use. Further, many of these prior art polyurethane materials are synthesized using a solvent, which can be detrimental if the resultant polyurethane material is used in applications necessitating a solvent-free polyurethane, i.e., protective devices such as condoms, gloves, and catheters. Thus, both safety and environmental considerations have necessitated a search for a waterborne, water-soluble, solvent-free polyurethane.

[0009] Also, these prior art waterborne polyurethane materials have been mechanically deficient in that they have not yielded a film having the requisite combination of high tensile strength, high percentage elongation and low modulus characteristic of natural or synthetic rubber. For example, **TABLE I** below, shows typical values of tensile strength, percentage elongation, and modulus for natural rubber.

TABLE I

PROPERTY	NATURAL RUBBER
Tensile strength, psi	4800
Elongation, %	840
100% Modulus, psi	125
300% Modulus, psi	200
500% Modulus, psi	600
750% Modulus, psi	2700

Waterborne prior art polyurethane materials, on the other hand, have not yielded the requisite combination of high tensile strength, high percentage elongation and low modulus characteristic of the natural or synthetic rubber set out in TABLE I.

[0010] Thus, there is a need for a solvent-free, or low solvent containing waterborne polyurethane, which can be used in the production of a film having a balance of high tensile strength, high percentage elongation and low modulus. The polyurethane film must have elastomeric properties like those attributed to rubber — that is, it must stretch under tension, have high tensile strength, retract rapidly, and give nearly complete recovery to its original dimensions.

Brief Summary of the Invention

[0011] The present invention provides a waterborne polyurethane useful as a film having elastomeric properties. More particularly, the film has a percentage elongation greater than 700%, a tensile strength greater than 4500 psi, a 100% modulus below 450 psi, a 300% modulus below 700 psi, and a 500% modulus below 1500 psi. The polyurethane can preferably be prepared in the absence of an organic solvent or in low solvent content media.

[0012] According to a first aspect of the invention, a waterborne polyurethane dispersion having elastomeric properties is provided. The polyurethane comprises the reaction product of (a) a polyisocyanate component; (b) an active hydrogen containing component, such as a polyol or a polyamide; and (c) a water-solubilizing compound having water-solubilizing groups to form an isocyanate terminal prepolymer, which is neutralized by reaction with a tertiary amine, dispersed in water, and the reaction product is then chain extended by reaction with a primary or secondary amine. The polyurethane dispersion is capable of forming a film having a tensile strength greater than about 3500 psi and a percentage elongation greater than about 700%. The polyurethane is prepared in a low cosolvent system, preferably in the absence of an organic solvent.

[0013] According to a second aspect of the invention, a waterborne polyurethane for use as a film having elastomeric properties is provided, the film having a tensile strength greater than about 3500 psi and a percentage elongation greater than about 700%. The film also has a 100% modulus below 450 psi, 300% modulus below 700 psi, and a 500% modulus below 1500 psi.

[0014] According to a third aspect of the invention, a film cast from a waterborne polyurethane dispersion is provided, the film having a percentage elongation greater than about 700% and a tensile strength greater than about 4500 psi. The film may be used in the manufacture of various products, particularly medical gloves, regular gloves, catheters, tubing and condoms, and the like products, which would benefit from being made from a polymer having the characteristics of the polymer of the present invention.

[0015] One advantage of the present invention is that a waterborne polyurethane dispersion can be used to produce a film having elastomeric properties.

[0016] Another advantage of the present invention is that a solvent-free waterborne polyurethane dispersion can be used to produce certain medical products, including gloves and condoms.

[0017] Another advantage of the present invention is that a waterborne polyurethane dispersion can be used to produce a film having both a percentage elongation greater than 700% and a tensile strength greater than 4500 psi.

[0018] Still another advantage of the present invention is that an elastomeric film cast from a polyurethane dispersion can be simply and economically manufactured.

[0019] Still another advantage of the present invention is that a waterborne polyurethane can be used to produce a film having mechanical properties comparable to rubber. Still another advantage of the present invention is that certain medical products, particularly gloves, condoms, catheters, and tubing can be produced from a material other than rubber.

[0020] Still a further advantage of the present invention is that a wide array of products can be simply and econom-

ically manufactured using an elastomeric film cast or dipped from a waterborne polyurethane dispersion or by using the polymer, i.e., the waterborne polyurethane dispersion, as a coating for textiles, such as backcoatings, fabric or fiber saturants, finishes, or transfer coatings, or other textile and non-textile applications where good elastomeric properties would be useful.

[0021] Still other benefits and advantages of the invention will become apparent to those skilled in the art upon a reading and understanding of the following detailed specification.

Detailed Description of the Preferred Embodiment

[0022] The present invention relates to a waterborne polyurethane polymer demonstrating film properties comparable to rubber. The waterborne polyurethane can be stabilized anionically, cationically, or non-ionically. The films of the present invention show elastic properties, i.e., mechanical properties comparable to rubber, including, when run at a gage length of one inch, a percentage elongation of greater than 700%; a tensile strength greater than 4500 psi; a 300% modulus below 700 psi; a 500% modulus below 1500 psi; little to no yield point; and, rapid recovery to original shape after stretching. Rubber-like properties (or comparable properties) are attributable to a film which can be stretched at room temperature to at least twice its original length and after having been stretched and the stress removed, will return with force to approximately its original length within a short time.

[0023] The terminology "percentage elongation", "tensile strength", "modulus of elasticity" and "yield point" are well-known to those skilled in the art. These are measured in accordance with ASTM (American Society for Testing and Materials) Standard D 2370-82. Percentage elongation is the fractional increase in a material's length due to stress in tension. Tensile strength is the maximum stress a material subjected to a stretching load can withstand without tearing. The modulus of elasticity is the ratio of the increment of some specified form of stress to the increment of some specified form of strain. Yield point is the lowest stress at which strain increases without increase in stress.

[0024] The waterborne polyurethane polymer of the present invention is synthesized by reacting a polyisocyanate with an active hydrogen containing, high molecular weight product, such as a long-chain polyol or a long-chain polyamide, and a water-solubilizing compound having water-solubilizing groups to form an isocyanate terminal prepolymer. The prepolymer is subsequently neutralized with a tertiary amine and dispersed in water. The dispersed prepolymer is then chain-extended using a functional primary and/or secondary amine having at least 2 active hydrogens.

[0025] Any organic polyisocyanate is believed to be suitable for use in the present invention. Particular isocyanates include aliphatic, cycloaliphatic, araliphatic, and aromatic polyisocyanates, used alone or in mixtures of two or more. The preferred polyisocyanate is a diisocyanate.

[0026] Specific examples of suitable aliphatic polyisocyanates include alpha,omega-alkylene diisocyanates having from 5 to 20 carbon atoms, for instance, hexamethylene 1,6-diisocyanate, 1,12-dodecane diisocyanate, 2,2,4-trimethylhexamethylene diisocyanate, 2,4,4-trimethyl-hexamethylene diisocyanate, 2-methyl-1,5-pentamethylene diisocyanate, and mixtures thereof.

[0027] Specific examples of suitable cycloaliphatic polyisocyanates include dicyclohexylmethane diisocyanate (commercially available as Desmodur™W from Bayer Coating Division), isophorone diisocyanate, 1,4-cyclohexane diisocyanate, 1,4-cyclohexane bis(methylene isocyanate), 1,3-bis(isocyanatomethyl) cyclohexane, and mixtures thereof.

[0028] Specific examples of suitable araliphatic polyisocyanates include m-tetramethyl xylylene diisocyanate, p-tetramethyl xylylene diisocyanate, 1,4-xylylene diisocyanate, 1,3-xylylene diisocyanate and mixtures thereof.

[0029] Examples of suitable aromatic diisocyanates include methane-bis(4-phenyl isocyanate), toluene diisocyanate and their isomers.

[0030] The preferred polyisocyanate is an aliphatic diisocyanate. Isophorone diisocyanate (IPDI) and an isomer blend of 2,2,4 and 2,4,4 trimethyl hexamethylene diisocyanate (TMDI), are the aliphatic diisocyanates of choice because of their inherent "softness" (low modulus films), low prepolymer viscosity for reduced co-solvent levels, and relatively high tensile strength capabilities. Other polyisocyanates may be used in whole or in part substitution to attain similar properties, but will lessen certain polymer qualities. For example, tetramethylxylylene diisocyanate (TMXDI) decreases tensile strength. Cyclomethyl bis-methylenisocyanate (H_{12} MDI) and methane-bis(4-phenyl isocyanate)(MDI) increase modulus. Toluene diisocyanate (TDI) works in the present invention if non-yellowing properties are not required.

[0031] The terminology "polyol" denotes any high molecular weight product, which has an active hydrogen component that can be reacted and includes materials having an average of about two or more hydroxyl groups per molecule. The long-chain polyol which can be used in the present invention includes higher polymeric polyols such as polyester polyols and polyether polyols, as well as other acceptable "polyol" reactants, which have an active hydrogen component such as polyester polyols, polyhydroxy polyester amides, hydroxyl containing polycaprolactones, hydroxy-containing acrylic interpolymer, hydroxy-containing epoxies, and hydrophobic polyalkylene ether polyols.

[0032] The polyester polyols are esterification products prepared by the reaction of organic polycarboxylic acids or their anhydrides with a stoichiometric excess of a polyol. Examples of suitable polyols for use in the reaction include polyglycol adipates, polyethylene terephthalate polyols, polycaprolactone polyols, orthophthalic polyols, and sulfonated

polyols, etc.

[0033] The polycarboxylic acids and polyols are typically aliphatic or aromatic dibasic acids and diols. The diols used in making the polyester include alkylene glycols, e.g., ethylene glycol, butylene glycol, neopentyl glycol and other glycols such as bisphenol A, cyclohexane diol, cyclohexane dimethanol, caprolactone diol, hydroxyalkylated bisphenols, and polyether glycols.

[0034] Suitable carboxylic acids include dicarboxylic acids and tricarboxylic acids, e.g., maleic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, azelaic acid, sebacic acid, chlorendic acid, 1,2,4-butane-tricarboxylic acid, phthalic acid, terephthalic acid, and the isomers of phthalic acid.

[0035] Preferably, the polyester polyol should be as non-crystalline as possible and in that regard should have a broad melting range and be liquid at 90°F or lower. The average molecular weight for the polyester polyol should be at least 2400 to afford high elongation and low tensile modulus at a given elongation. The preferred molecular weight for the polyols and polyamides used in this invention is from about 2900 to about 5500 Daltons.

[0036] The preferred polyester polyol is a diol. More particularly, it is a hexane diol neopentyl glycol adipic acid polyester diol — e.g., 67-3000 HNA (Pioneer Plastics) and 67-1000 HNA (Pioneer Plastics). Other preferred polyester diols include Rucoflex® 1015-35 (RUCO Polymer Corp.) and Rucoflex® 1043-35 (RUCO Polymer Corp.).

[0037] Polyether diols may be substituted in whole or in part; however, larger amounts of polyether diols tend to lower tensile strength. The use of the Acclaim® 3201 series (Arco Chemical), an improved polyether diol with a lower monol content, does not significantly reduce tensile strength as would conventional polyether diols. In addition, these polyether diols give significantly lower prepolymer viscosities, which allow for the manufacture of cosolvent free, low modulus urethanes.

[0038] Instead of a long-chain polyol, a long-chain amine may also be used in the practice of the present invention. Suitable amines include: Jeffamine® D-2000 and D-4000, which are amine-terminated polypropylene glycols, differing only by molecular weight, and which are available from Huntsman Chemical Company. It is also recognized that other difunctional active hydrogen containing materials in a suitable molecular weight range (averaging from about 2500 to about 5500 amu), may be suitable for this application.

[0039] To enhance the water-solubility, a water-solubilizing compound bearing a group that is water-soluble or can be made water-soluble is incorporated into the polymer chain. One particularly preferred water-solubilizing compound is 2,2-bis(hydroxymethyl) propionic acid — also known as dimethylol propanoic acid (DMPA). Other suitable water-solubilizing compounds would include the following: tartaric acid, dimethylol butanoic acid (DMBA), glycolic acid, thioglycolic acid, lactic acid, malic acid, dihydroxy malic acid, dihydroxy tartaric acid, and 2,6-dihydroxy benzoic acid.

[0040] Water-solubilizing groups are incorporated in the prepolymer in an inactive form in the water-solubilizing compound and activated by a salt-forming compound such as a tertiary amine. The water-solubilizing groups are hydrophilic or ionic groups whose presence in the polymer assists solubility or dispersability of the polymer in water and enhances the stability of polymer dispersions. Polyurethanes are generally hydrophobic and not water-dispersable.

[0041] The formation of the isocyanate terminal prepolymer may be achieved without the use of a catalyst. However, a catalyst is preferred. Examples of suitable catalysts include stannous octoate, dibutyl tin dilaurate and tertiary amine compounds such as triethyl amine and bis(dimethylaminoethyl) ether, morpholine compounds such as β,β' -dimorpholinodiethyl ether, bismuth carboxylates, zinc-bismuth carboxylates, iron (III) chloride, potassium octoate, potassium acetate, and DABCO® (bicycloamine). The preferred catalyst is FASCAT® 2003 from Atochem. The amount of catalyst used is typically 10-40 parts per million of the isocyanate terminal prepolymer.

[0042] A prepolymer diluent may be used to render the viscosity of the copolymer dispersion low enough to process the product. The preferred prepolymer diluent is N-methyl pyrrolidinone (NMP), because it does not contain reactive groups, which will interfere with the reaction. It is preferred that a minimal amount of the N-methyl pyrrolidinone (NMP) be used, preferably in a range of 0-10% N-methyl pyrrolidinone (NMP) by weight of the polyurethane dispersion. The maximum amount of N-methyl pyrrolidinone (NMP) used is preferably 10.0% by weight of the resultant waterborne polyurethane dispersion.

[0043] However, the copolymer dispersion is preferably prepared in the absence of a diluent. In this case, the prepolymer should be made in a way that will minimize its resultant viscosity. In neat (no solvent) and solution polymers, viscosity is largely determined by the molecular weight of the polymer. To minimize the molecular weight of a finished prepolymer, an NCO/OH ratio of 2/1 should be used. In this way the diol portions are essentially endcapped by the diisocyanate species, leaving an isocyanate terminal prepolymer of relatively low viscosity. As the NCO/OH ratio of a prepolymer is reduced, the resultant viscosity increases dramatically. It is recognized that cosolvent free materials can be made at below 2/1 NCO/OH ratios, but they become more difficult to process, pump, stir, etc. Also, higher temperatures will be needed to work with such a prepolymer.

[0044] As the NCO/OH ratio of a prepolymer is increased above 2/1, the molecular weight will be limited as with the 2/1 ratio, but the excess diisocyanate will function as a diluent, further reducing viscosity. While this is a desired effect, raising the NCO/OH ratio above 2/1 can also have negative effects. When isocyanate content of a polyurethane is increased, the hardness, or modulus of the polyurethane, along with the yield point, is increased. This is undesirable

for producing a "rubbery" polymer. Also, when excess diisocyanate (obtained from using an NCO/OH ratio much greater than 2/1) is introduced into a dispersion, and this dispersion is then extended with a primary (or secondary) amine, high molecular weight polyureas may be formed. These materials are not soluble, but by controlling the ratio in the range of 1.8 to 2.3 the results will be satisfactory. If an excess of isocyanate is used the result may be gels or grittiness in a cast film, and sediment in the dispersion. This can lead to weakened films, which have a poor appearance. For these reasons, an NCO/OH ratio of about 1.8/1 to 2.3/1 are desirable, and ratios of about 1.9/1 to 2.1/1 are most desirable.

[0045] Another important factor in keeping prepolymer viscosity low is in the selection of raw materials, and the amounts in which they are used. The preferred isocyanates for this invention are isophorone diisocyanate and 2,2,4 and/or 2,4,4, trimethyl hexamethylene diisocyanate, due to their positive effects (high strength, low modulus, low prepolymer viscosity) on processing and film properties. To further reduce prepolymer viscosity, a polyether polyol may be substituted in whole or in part for a polyester polyol. The preferred polyether polyol is Acclaim 3201, due to its low viscosity when reacted into a prepolymer, and due to its low monol content vs. conventional polyethers.

[0046] The acid content of the water-solubilizing compound is yet another consideration for producing a low viscosity prepolymer. Higher acid numbers will lead to higher viscosity, but there is also a minimum amount of acid needed to render a given polyurethane backbone dispersable. The preferred carboxyl containing diol in this invention is dimethylol propionic acid. The preferred range of carboxyl containing diol or water-solubilizing compound is from about 2 wt.% to about 4 wt.% of the total prepolymer. The amount used will approach 2 wt.% as the backbone becomes more hydrophilic, as with higher concentrations of polyether diol. As the backbone becomes more hydrophobic, as with polyester based systems, the acid content needed for dispersion will approach 3-4 wt.%.

[0047] Neutralization of the prepolymer having dependent carboxyl groups with the tertiary amine converts the carboxyl groups to carboxylate anions, thus having a solubilizing effect. Suitable tertiary amines, which can be used to neutralize the polymer include triethyl amine (TEA), dimethyl ethanol amine (DMEA), and N-methyl morpholine. The preferred tertiary amine is triethyl amine (TEA). It is recognized that primary or secondary amines may be used in place of tertiary amines, if they are sufficiently hindered to avoid interfering with the chain extension process.

[0048] As a chain extender, any organic 2+ (i.e., having 2 or more) functional primary and/or secondary amine would be suitable for use in the present invention. Suitable organic amines for use as a chain extender include diethylene triamine (DETA), ethylene diamine (EDA), meta-xylylene diamine (MXDA), and aminoethyl ethanolamine (AEEA). Also suitable for practice in the present invention are propylene diamine, butylene diamine, hexamethylene diamine, cyclohexylene diamine, phenylene diamine, tolylene diamine, xylylene diamine, 3,3-dichlorobenzidine, 4,4-methylene-bis (2-chloroaniline), and 3,3-dichloro-4,4-diamino diphenylmethane.

[0049] Hydrazine, an inorganic amine, is preferably used to finish off any excess extension necessary. Other suitable inorganic amines would include ammonia, substituted hydrazines, and hydrazine reaction products.

[0050] A degree of branching of the polymer may be beneficial, but is not required to maintain a high tensile strength and improve resistance to creep — that is, recovery to that or near its original length after stretching. This degree of branching may be accomplished during the prepolymer step or the extension step. For branching during the extension step, the chain extender DETA is preferred, but other 2+ (two or more) functional amines may also be used in conjunction with ring-structured diamines, e.g., Metaxylenediamine (MXDA).

[0051] For pre-polymer branching, it is preferred that trimethylol propane (TMP) and other 2+ functional diols be used. Higher functional 2+ isocyanates may alternatively be used.

[0052] The branching monomers should be present in amounts from about .5 wt. % to 4 wt. % of the polymer backbone. Preferably, the requisite degree of branching needed is obtained during the extension step rather than during the prepolymer step. Otherwise, the high viscosity of the prepolymer, which results due to the branching, must be accounted for during the extension step.

[0053] The invention will now be described in detail in the following examples.

EXAMPLE I

[0054] **PREPOLYMER STEP:** The following materials were charged to a reactor: 2039.92 grams (.474 eq.) 67-3000 HNA (Pioneer Plastics); and 59.47 grams (.046 eq.) 67-1000 HNA (Pioneer Plastics). The mixer was then turned on and 530.35 grams (1.70 eq.) of isophorone diisocyanate (IPDI) was added to the reactor. At this point, heat was applied to the batch to raise the temperature to over 200°F. After about 35 minutes at over 200°F, 480 grams of N-methyl pyrrolidinone (NMP), followed by 90.26 grams (.48 eq.) dimethylol propanoic acid (DMPA) were charged. The resultant mixture was allowed to react for about two hours, at about 190-200°F. The percent NCO remaining was then measured using a titration with dibutylamine (DBA) and 1.0M HCl. The result is a finished prepolymer which may be immediately extended, as set forth below, or stored under a nitrogen cap at 120°F. **EXTENSION STEP:** 600 grams of the prepolymer were warmed to 142°F and 15.34 grams triethyl amine (TEA) were charged to the batch. When the TEA was thoroughly mixed, 512.8 grams of the prepolymer were charged to a vessel containing 412 grams water at 82°F. 12.05 grams N-

methyl pyrrolidinone (NMP) were charged to the batch and allowed to mix for 15 minutes. Chain extension was then accomplished by charging a blend containing 4.47 grams meta-xylene diamine (MXDA)/2.26 grams diethylenetriamine (DETA)/15.72 grams H₂O. A small amount of hydrazine (3.58 grams) was added to complete chain extension. The result is a polymer which can be used or stored under a nitrogen cap.

EXAMPLE II

[0055] The finished prepolymer of Example I was also chain extended as shown below.

[0056] **EXTENSION STEP:** 600 grams of the prepolymer of Example I were warmed to 144°F and 15.34 grams of TEA were charged to the batch. When the TEA was thoroughly mixed, 512.8 grams of the prepolymer were charged to a vessel containing 414 grams water at 78°F. 12.05 grams of NMP were charged to the batch and allowed to mix for 15 minutes. Chain extension was then accomplished by charging a blend containing 2.68 grams of MXDA, 1.36 grams of DETA, and 9.44 grams of H₂O. A small amount of hydrazine (3.75 grams) was added to complete chain extension. The result is a polymer product.

EXAMPLE III

[0057] **PREPOLYMER STEP:** The following materials were charged to a reactor: 1883.51 grams (.450 eq.) 1015-35 (RUCO Polymer Corp.); and 84.67 grams (.070 eq.) 67-1000 HNA (Pioneer Plastics). The mixer was then turned on and 497.20 grams (1.70 eq.) of IPDI was added to the reactor. At this point, heat was applied to the batch to raise the temperature to over 200°F. Once the exotherm began to subside, three drops FASCAT® 2003 (Atochem) catalyst were charged. After about thirty minutes at over 200°F, 450 grams of NMP, followed by 84.62 grams (.48 eq.) DMPA were charged. The resultant mixture was allowed to react for about two hours at about 190-200°F. The percent NCO remaining was then measured using a titration with DBA and HCl. The result is a finished prepolymer.

[0058] **EXTENSION STEP:** 800 grams of the prepolymer were warmed to 142°F and 20.45 grams triethyl amine (TEA) were charged to the batch. When the TEA was thoroughly mixed, 717.4 grams of the prepolymer were charged to a vessel containing 586 grams water at 97°F. 16.87 grams N-methyl pyrrolidinone (NMP) were charged to the batch and allowed to mix for 15 minutes. Chain extension was then accomplished by charging a blend containing 8.72 grams meta-xylene diamine (MXDA)/8.82 grams DETA/17.54 grams H₂O. The result is a polymer product.

EXAMPLE IV

[0059] **PREPOLYMER STEP:** The following materials were charged to a reactor: 408.09 grams (.450 eq.) 1015-35 (RUCO Polymer Corp.) and 18.35 grams (.070 eq.) 67-1000 HNA (Pioneer Plastics). The mixer was then turned on and 107.73 grams (1.70 eq.) of isophorone diisocyanate (IPDI) was added to the reactor. At this point, heat was added to the batch to raise the temperature to over 200°F. Once the exotherm began to subside, one drop FASCAT® 2003 (Atochem) catalyst was charged. After about thirty minutes at over 200°F, 97.50 grams of N-methyl pyrrolidinone (NMP), followed by 18.33 grams (.48 eq.) dimethylol propanoic acid (DMPA) were charged. The resultant mixture was allowed to react for about two hours, at about 190-200°F. The percent NCO remaining was then measured using a titration with dibutylamine (DBA) and HCl. The result is a finished prepolymer.

[0060] **EXTENSION STEP:** 640 grams of the prepolymer were warmed to 158°F and 16.35 grams triethyl amine (TEA) were charged to the batch. When the TEA was thoroughly mixed, 564.1 grams of the prepolymer were charged to a vessel containing 457.19 grams water at 76°F. 13.25 grams N-methyl pyrrolidinone (NMP) were charged to the batch and allowed to mix for 15 minutes. Chain extension was then accomplished by charging a blend containing 6.49 grams meta-xylene diamine (MXDA)/3.28 grams DETA/16.34 grams water. The result is the polymer product.

EXAMPLE V

[0061] **PREPOLYMER STEP:** The following materials were charged to a reactor: Half of a total of 335.56 grams (.25 eq.) Acclaim 3201 (Arco Chemical); 195.73 grams isophorone diisocyanate (IPDI); and 31.86 grams (.54 eq.) dimethylol propanoic acid (DMPA). Heat was applied to raise the batch to approximately 187°F and then turned off. At approximately 208°F, 39.63 additional grams of the Acclaim 3201 were charged to the reactor. At about 205°F, 5.42 additional grams of the Acclaim 3201 were charged to the reactor. At about 194°F, one drop FASCAT® 2003 was charged to the reactor. The remainder of the Acclaim 3201 was then charged to the reactor. At 210°F, 106.7 grams of a total 286.86 grams 67-3000 HNA (Pioneer Plastics) was charged to the reactor. Within about five minutes, the remainder of the 67-3000 HNA was charged to the reactor. Once the reaction reached about 196°F, another drop of FASCAT® 2003 was charged to the reactor. The resultant mixture was allowed to react for about a half hour, at about 190-200°F. The percent NCO remaining was then measured using a titration with dibutylamine (DBA) and HCl.

EP 1 027 381 B1

[0062] **EXTENSION STEP:** 140 grams of the prepolymer were warmed to 148°F. They were then charged to a vessel containing 199.32 grams water and 4.36 grams TEA at 62°F and allowed to mix for 15 minutes. Chain extension was then accomplished by charging a blend containing 1.11 grams MXDA/56 grams DETA/8.35 grams water. A small amount of 35% hydrazine (3.80 grams) was added to complete chain extension. The resultant polymer can be used or can be stored under a nitrogen cap.

EXAMPLE VI

[0063] The finished prepolymer of Example V was chain extended as shown below.

[0064] **EXTENSION STEP:** Approximately two hours after the prepolymer was formed, 140 grams of the prepolymer of Example V were warmed to 155°F. The prepolymer was then charged to a vessel containing 204.97 grams water and 4.36 grams TEA at 65°F and allowed to mix for 15 minutes. Chain extension was then accomplished by charging 5.30 grams 35% hydrazine. The resultant product is a polymer.

EXAMPLE VII

[0065] **PREPOLYMER STEP:** The following materials were charged to a reactor: 421.78 grams (.400 eq.) 1043-35 (RUCO Polymer Corp.); 110.12 grams (.105 eq.) Acclaim 3201 (Arco Chemical); 86.68 grams (1.20 eq.) TMDI; and 53.53 grams (.70 eq.) isophorone diisocyanate (IPDI), warmed to about 207°F, followed by shutting off the heat. When the reactor reached about 214°F, one drop FASCAT® 2003 was charged to the reactor followed by 22.82 grams (.495 eq.) dimethylol propanoic acid (DMPA). The resultant mixture was allowed to react for about one and one half hours, at about 200°F. The percent NCO remaining was then measured using a titration with dibutylamine (DBA) and HCl. The result is a finished prepolymer.

[0066] **EXTENSION STEP:** The finished prepolymer was warmed to 204°F. 306.7 grams of the prepolymer were charged to a vessel containing 284.38 grams of water at 71°F and allowed to mix for 15 minutes. Chain extension was then accomplished by charging a blend containing 4.46 grams EDA/13.38 grams water. A blended mixture containing .53 grams EDA and 3 grams water was then charged to the reactor followed by charging 1.5 grams TEA to the reactor. The result was a polymer.

EXAMPLES VIII-XIV

[0067] Each of the polyurethane dispersions of Examples I-VII was drawn down on Mylar® made of polyethylene terephthalate at approximately 8 wet mils and through-dried at ambient temperature. The Mylar® and polyurethane were then dried for three minutes at 300°F in an oven. After drying, a 24-hour delay passed to allow the polyurethane to equilibrate at ambient temperature. The Mylar® was then cut into 1 inch wide strips. The dried polyurethane film was removed from the Mylar® and its thickness was measured.

[0068] Samples of the cured polyurethane film were then tested in the Instron tensile to measure various properties, including tensile strength, percentage elongation, and modulus. The interface type of the Instron was a Series 42/43/4400. The machine parameters of the test were set at a sample rate of 10 cm/sec and a cross-set speed of 2 in./min. Humidity was at 50% and the ambient temperature was 72°F.

[0069] Measurements of tensile strength at breaking, percentage elongation, and modulus of elasticity corresponding to samples of polyurethane film cast from the polyurethane dispersions of Examples I-VII are recorded in TABLES II-A through VIII-B below.

TABLE II-A

DIMENSIONS	SPECIMEN 1 ^a	SPECIMEN 2 ^a
WIDTH (in.)	1.0000	1.0000
THICKNESS (in.)	.00270	.00290
SPEC. GAUGE LEN (in.)	2.0000	2.0000
GRIP DISTANCE (in.)	2.0000	2.0000

^aSpecimens 1 and 2 correspond to a film cast from the polyurethane dispersion of Example I.

EP 1 027 381 B1

TABLE II-B

	SPECIMEN 1 ^a	SPECIMEN 2 ^a
TENSILE AT MAX LOAD (psi)	4826	4334
ELONGATION (%)	767.5	740.0
STRESS AT 10% ELONGATION (psi)	146.2	149.1
STRESS AT 50% ELONGATION (psi)	288.3	276.5
STRESS AT 100% ELONGATION (psi)	352.0	331.0
STRESS AT 300% ELONGATION (psi)	603.1	538.6
STRESS AT 400% ELONGATION (psi)	851.0	795.6
STRESS AT 500% ELONGATION (psi)	1264	1212

^aSpecimens 1 and 2 correspond to a film cast from the polyurethane dispersion of Example I.

TABLE III-A

DIMENSIONS	SPECIMEN 1 ^a	SPECIMEN 2 ^a
WIDTH (in.)	1.0000	1.0000
THICKNESS (in.)	.00270	.00270
SPEC. GAUGE LEN (in.)	2.000	2.000
GRIP DISTANCE (in.)	2.000	2.000

^aSpecimens 1 and 2 correspond to a film cast from the polyurethane dispersion of Example II.

TABLE III-B

	SPECIMEN 1 ^a	SPECIMEN 2 ^a
TENSILE AT MAX LOAD (psi)	4037	4419
ELONGATION (%)	767.0	797.5
STRESS AT 10% ELONGATION (psi)	113.3	107.4
STRESS AT 50% ELONGATION (psi)	240.6	226.7
STRESS AT 100% ELONGATION (psi)	298.3	280.4
STRESS AT 300% ELONGATION (psi)	524.1	485.6
STRESS AT 400% ELONGATION (psi)	740.5	697.1
STRESS AT 500% ELONGATION (psi)	1096.0	1049.0

^aSpecimens 1 and 2 correspond to a film cast from the polyurethane dispersion of Example II.

TABLE IV-A

DIMENSIONS	SPECIMEN 1 ^a	SPECIMEN 2 ^a
WIDTH (in.)	1.0000	1.0000
THICKNESS (in.)	.00250	.00280
SPEC. GAUGE LEN (in.)	2.0000	1.0000
GRIP DISTANCE (in.)	2.0000	1.0000

^aSpecimens 1 and 2 correspond to a film cast from the polyurethane dispersion of Example III.

EP 1 027 381 B1

TABLE IV-B

	SPECIMEN 1 ^a	SPECIMEN 2 ^a
TENSILE AT MAX LOAD (psi)	4812	4771
ELONGATION (%)	756.0	870.4
STRESS AT 10% ELONGATION (psi)	121.8	161.1
STRESS AT 50% ELONGATION (psi)	245.2	294.7
STRESS AT 100% ELONGATION (psi)	318.3	371.4
STRESS AT 300% ELONGATION (psi)	616.0	660.3
STRESS AT 400% ELONGATION (psi)	851.7	827.8
STRESS AT 500% ELONGATION (psi)	1242	1120

^aSpecimens 1 and 2 correspond to a film cast from the polyurethane dispersion of Example III.

TABLE V-A

DIMENSIONS	SPECIMEN 1 ^a
WIDTH (in.)	1.0000
THICKNESS (in.)	.00300
SPEC. GAUGE LEN (in.)	2.0000
GRIP DISTANCE (in.)	2.0000

^aSpecimen 1 corresponds to a film cast from the polyurethane dispersion of Example IV.

TABLE V-B

	SPECIMEN 1 ^a
TENSILE AT MAX LOAD (psi)	4393
ELONGATION (%)	726.5
STRESS AT 10% ELONGATION (psi)	148.9
STRESS AT 50% ELONGATION (psi)	282.7
STRESS AT 100% ELONGATION (psi)	359.7
STRESS AT 300% ELONGATION (psi)	688.2
STRESS AT 400% ELONGATION (psi)	906.2
STRESS AT 500% ELONGATION (psi)	1312

^aSpecimen 1 corresponds to a film cast from the polyurethane dispersion of Example IV.

TABLE VI-A

DIMENSIONS	SPECIMEN 1 ^a
WIDTH (in.)	1.0000
THICKNESS (in.)	.00190
SPEC. GAUGE LEN (in.)	1.0000
GRIP DISTANCE (in.)	1.0000

^aSpecimen 1 corresponds to a film cast from the polyurethane dispersion of Example V.

EP 1 027 381 B1

TABLE VI-B

	SPECIMEN 1 ^a
TENSILE AT MAX LOAD (psi)	5621
ELONGATION (%)	1030
STRESS AT 10% ELONGATION (psi)	135.6
STRESS AT 50% ELONGATION (psi)	281.8
STRESS AT 100% ELONGATION (psi)	350.4
STRESS AT 300% ELONGATION (psi)	627.1
STRESS AT 400% ELONGATION (psi)	853.1
STRESS AT 500% ELONGATION (psi)	1130

^aSpecimen 1 corresponds to a film cast from the polyurethane dispersion of Example V.

TABLE VII-A

DIMENSIONS	SPECIMEN 1 ^a	SPECIMEN 2 ^a
WIDTH (in.)	1.0000	1.0000
THICKNESS (in.)	.00190	.00200
SPEC. GAUGE LEN (in.)	1.0000	1.0000
GRIP DISTANCE (in.)	1.0000	1.0000

^aSpecimens 1 and 2 correspond to a film cast from the polyurethane dispersion of Example VI.

TABLE VII-B

	SPECIMEN 1 ^a	SPECIMEN 2 ^a
TENSILE AT MAX LOAD (psi)	5947.0	5870.0
ELONGATION (%)	1195.0	1190.0
STRESS AT 10% ELONGATION (psi)	129.3	123.8
STRESS AT 50% ELONGATION (psi)	283.2	263.1
STRESS AT 100% ELONGATION (psi)	366.7	329.0
STRESS AT 300% ELONGATION (psi)	594.5	548.6
STRESS AT 400% ELONGATION (psi)	755.0	715.0
STRESS AT 500% ELONGATION (psi)	961.9	922.7

^aSpecimens 1 and 2 corresponds to a film cast from the polyurethane dispersion of Example VI.

TABLE VIII-A

DIMENSIONS	SPECIMEN 1 ^a
WIDTH (in.)	1.0000
THICKNESS (in.)	.00410
SPEC. GAUGE LEN (in.)	1.0000
GRIP DISTANCE (in.)	1.0000

^aSpecimen 1 corresponds to a film cast from the polyurethane dispersion of Example VII.

TABLE VIII-B

	SPECIMEN 1 ^a
TENSILE AT MAX LOAD (psi)	4854
ELONGATION (%)	1715.00
STRESS AT 10% ELONGATION (psi)	90.37
STRESS AT 50% ELONGATION (psi)	205.6
STRESS AT 100% ELONGATION (psi)	255.4
STRESS AT 300% ELONGATION (psi)	378.5
STRESS AT 400% ELONGATION (psi)	436.1
STRESS AT 500% ELONGATION (psi)	498.9

^aSpecimen 1 corresponds to a film cast from the polyurethane dispersion of Example VII.

[0070] As can be appreciated, the present invention is useful for a wide array of products that can be simply and economically manufactured using an elastomeric film cast or dipped from a waterborne polyurethane dispersion or by using the polymer, i.e., the waterborne polyurethane dispersion, as a coating for textiles, such as backcoatings, fabric or fiber saturants, finishes, or transfer coatings, or other textile and non-textile applications where good elastomeric properties would be useful. The film can be prepared in the absence of a solvent, thus making it attractive for a variety of protection products for medical and industrial applications such as gloves, condoms, catheters, and the like.

[0071] The invention has been described with reference to preferred and alternate embodiments. Obviously, modifications and alterations will occur to others upon the reading and understanding of this specification. It is intended to include all such modifications and alterations insofar as they come within the scope of the appended claims or the equivalents thereof.

Claims

1. A waterborne polyurethane wherein the polyurethane comprises the reaction product of

(a) a polyisocyanate component selected from the group consisting of an aliphatic polyisocyanate, an aromatic polyisocyanate, a cycloaliphatic polyisocyanate, and an araliphatic polyisocyanate;

(b) a long-chain, active hydrogen containing material, containing 2 or more active hydrogens per molecule selected from the group consisting of a polyamide, a polyester polyol, a polycarbonate polyol, a polyether polyol and mixtures thereof, and an amine-terminated polypropylene glycol; and

(c) a water-solubilizing compound having water-solubilizing groups selected from the group consisting of dimethylol propanoic acid, tartaric acid, dimethylol butanoic acid, glycolic acid, thioglycolic acid, lactic acid, malic acid, dihydroxymalic acid, dihydroxytartaric acid, and 2,6-dihydroxybenzoic acid present in a range of from 2 wt.% to 4 wt.% of the total prepolymer.

to form an isocyanate prepolymer, having a NCO to OH ratio of 1.3/1 to 4.0/1, which is neutralized by reaction with a tertiary amine, dispersed in water, and chain extended by reaction with an amine, said polyurethane when in the form of a film, having elastic properties (as measured in accordance with ASTM D 2370-82) comparable to rubber, a tensile strength greater than 24.19 MPa (3500 psi), a 100% modulus below 3.10 MPa (450 psi), a 500% modulus below 10.34 MPa (1500 psi), and a percentage elongation greater than 700% at 22.2°C (72°F).

2. The polyurethane of claim 1 wherein the polyisocyanate is a diisocyanate.

3. The polyurethane of claim 1 wherein the NCO to OH ratio of the prepolymer is 1.4/1 to 3.0/1.

4. The polyurethane of claim 1 wherein the NCO to OH ratio of the prepolymer is 1.8/1 to 2.3/1.

5. The polyurethane of claim 1 wherein the NCO to OH ratio of the prepolymer is 1.9/1 to 2.1/1.

6. The polyurethane of claim 2 wherein the diisocyanate is one selected from the group consisting of isophorone diisocyanate, 2,2,4 trimethyl hexamethylene diisocyanate, 2,4,4 trimethyl hexamethylene diisocyanate and mixtures thereof.
7. The polyurethane of claim 2 wherein the diisocyanate is one selected from the group consisting of tetramethylxylene diisocyanate (TMXDI), cyclohexyl, bis-methylenisocyanate (H₁₂MDI), methane-bis(4-phenyl isocyanate) (MDI), toluene diisocyanate (TDI), 2,2,4 and 2,4,4 isomer blend of trimethyl hexamethylene diisocyanate (TMDI) and mixtures thereof.
8. The polyurethane of claim 1 wherein the polyester polyol is one selected from the group consisting of a hexanediol neopentyl glycol adipate, ethylene glycol/diethylene glycol adipate, and ethylene glycol/butane diol adipate, and mixtures thereof.
9. The polyurethane of claim 1 wherein the long-chain polyester polyol has an average molecular weight from 2900 to 5500 Daltons.
10. The polyurethane of claim 1 wherein the polyether polyol is one selected from the group consisting of poly-ethylene oxide, poly-propylene oxide, and mixtures thereof.
11. The polyurethane of claim 1 wherein the long-chain amide is an amine-terminated polypropylene glycol.
12. The polyurethane of claim 1 wherein the water-solubilizing compound is dimethylol propanoic acid.
13. The polyurethane of claim 1 wherein the amine for chain extension is one selected from the group consisting of primary amines, secondary amines, inorganic amines and mixtures thereof.
14. The polyurethane of claim 1 wherein the amine for chain extension is one selected from the group consisting of diethylenetriamine, ethylene diamine, metaxylenediamine, aminoethylethanolamine, hydrazine and mixtures thereof.
15. The polyurethane of claim 1 wherein the tertiary amine is one selected from the group consisting of triethylamine, dimethylethanol amine, and N-methylmorpholine.
16. The polyurethane of claim 1 wherein the film further comprises a 100% modulus below 2.76 MPa (400 psi), a 300% modulus below 4.83 MPa (700 psi) and a 500% modulus below 10.34 MPa (1500 psi) at 22.2°C (72°F).
17. The polyurethane of claim 1 wherein the polyurethane is prepared in the absence of a solvent.
18. The waterborne polyurethane according to claim 1 wherein the polyisocyanate component is selected from the group consisting of isophorone diisocyanate, hexamethylene 1,6-diisocyanate, 1,12-dodecane diisocyanate, 2,2,4-trimethyl-hexamethylene diisocyanate, 2,4,4-trimethyl-hexamethylene diisocyanate, 2-methyl-1,5-pentamethylene diisocyanate, 2,2,4 and 2,4,4 isomer blend of trimethyl hexamethylene diisocyanate and mixtures thereof;
the long-chain, active hydrogen containing material is a polyester polyol having an average molecular weight from 2900 to 5500 Daltons, and being a liquid at 32.2°C (90°F) or lower; and
the NCO to OH ratio is 1.8/1 to 2.3/1.
19. A waterborne polyurethane dispersion comprising the waterborne polyurethane as defined in any one of claims 1 to 18.
20. A film cast from the waterborne polyurethane dispersion as defined in claim 19, said film having elastic properties (as measured in accordance with ASTM D 2370-82) comparable to rubber, a tensile strength greater than 24.19 MPa (3500 psi), a 100% modulus below 3.10 MPa (450 psi), a 500% modulus below 10.34 MPa (1500 psi) and a percentage elongation greater than 700% at 22.2°C (72°F).
21. The film of claim 20 wherein the film is prepared in the absence of a solvent.
22. Medical gloves comprising the film of claim 20.

23. Contraceptive devices comprising the film of claim 20.

24. A catheter comprising the film of claim 20.

Revendications

1. Polyuréthane en phase aqueuse dans lequel le polyuréthane comprend le produit de la réaction

(a) d'un composant de polyisocyanate choisi dans le groupe constitué d'un polyisocyanate aliphatique, d'un polyisocyanate aromatique, d'un polyisocyanate cycloaliphatique et d'un polyisocyanate araliphatique; (b) d'un matériau à longue chaîne contenant de l'hydrogène actif, contenant 2 atomes d'hydrogène actif ou plus par molécule, choisi dans le groupe constitué d'un polyamide, d'un polyesterpolyol, d'un polycarbonate-polyol, d'un polyétherpolyol et de leurs mélanges, et d'un polypropylèneglycol à terminaison amine; et (c) d'un composé de solubilisation dans l'eau ayant des groupes de solubilisation dans l'eau choisis dans le groupe constitué de l'acide diméthylolpropanoïque, de l'acide tartrique, de l'acide diméthylol butanoïque, de l'acide glycolique, de l'acide thioglycolique, de l'acide lactique, de l'acide malique, de l'acide dihydroxymalique, de l'acide dihydroxytartrique et de l'acide 2,6-dihydroxybenzoïque présent dans une plage de 2% à 4% en poids du pré-polymère total,

pour former un pré-polymère d'isocyanate ayant un rapport de NCO à OH de 1,3/1 à 4,0/1, qui est neutralisé par réaction avec une amine tertiaire, dispersé dans l'eau et allongé en chaîne par réaction avec une amine, ledit polyuréthane, lorsqu'il se présente sous la forme d'un film, ayant des propriétés élastiques (mesurées selon la norme ASTM D 2370-82) comparables à celles du caoutchouc, une résistance à la traction supérieure à 24,19 MPa (3500 psi), un module à 100% inférieur à 3,10 MPa (450 psi), un module à 500% inférieur à 10,34 MPa (1500 psi) et un pourcentage d'allongement supérieur à 700% à 22,2°C (72°F).

2. Polyuréthane selon la revendication 1, dans lequel le polyisocyanate est un diisocyanate.

3. Polyuréthane selon la revendication 1, dans lequel le rapport de NCO à OH du pré-polymère est de 1,4/1 à 3,0/1.

4. Polyuréthane selon la revendication 1, dans lequel le rapport de NCO à OH du pré-polymère est de 1,8/1 à 2,3/1.

5. Polyuréthane selon la revendication 1, dans lequel le rapport de NCO à OH du pré-polymère est 1,9/1 à 2,1/1.

6. Polyuréthane selon la revendication 2, dans lequel le diisocyanate est un diisocyanate choisi dans le groupe constitué du diisocyanate d'isophorone, du diisocyanate de 2,2,4-triméthyl hexaméthylène, du diisocyanate de 2,4,4-triméthylhexaméthylène et de leurs mélanges.

7. Polyuréthane selon la revendication 2, dans lequel le diisocyanate est un diisocyanate choisi dans le groupe constitué du diisocyanate de tétraméthylxylène (TMXDI), du bis-méthylènisocyanate de cyclohexyle (H₁₂MDI), du méthane-bis(4-phényl-isocyanate) (MDI), du diisocyanate de toluène (TDI), d'un mélange d'isomères 2,2,4 et 2,4,4 de diisocyanate de triméthylhexaméthylène (TMDI) et de leurs mélanges.

8. Polyuréthane selon la revendication 1, dans lequel le polyester polyol est un polyester polyol choisi dans le groupe constitué d'un adipate d'hexanediol et de néopentylglycol, d'un adipate d'éthylèneglycol/diéthylèneglycol et d'un adipate d'éthylèneglycol/butanediol et de leurs mélanges.

9. Polyuréthane selon la revendication 1, dans lequel le polyester polyol à longue chaîne a un poids moléculaire moyen dans la plage de 2900 à 5500 daltons.

10. Polyuréthane selon la revendication 1, dans lequel le polyéther polyol est un polyol choisi dans le groupe constitué du poly(oxyde d'éthylène, du poly(oxyde de propylène) et de leurs mélanges.

11. Polyuréthane selon la revendication 1, dans lequel l'amide à longue chaîne est un polypropylèneglycol à terminaison amine.

12. Polyuréthane selon la revendication 1, dans lequel le composé de solubilisation dans l'eau est l'acide diméthylol-

propanoïque.

13. Polyuréthane selon la revendication 1, dans lequel l'amine pour l'allongement de chaîne est une amine choisie dans le groupe constitué des amines primaires, des amines secondaires, des amines inorganiques et de leurs mélanges.

14. Polyuréthane selon la revendication 1, dans lequel l'amine pour l'allongement de chaîne est une amine choisie dans le groupe constitué de la diéthylènetriamine, de l'éthylènediamine, de la métaxylylènediamine, de l'aminéthyléthanolamine, de l'hydrazine et de leurs mélanges.

15. Polyuréthane selon la revendication 1, dans lequel l'amine tertiaire est une amine choisie dans le groupe constitué de la triéthylamine, de la diméthyléthanolamine et de la N-méthylmorpholine.

16. Polyuréthane selon la revendication 1, dans lequel le film comprend en outre un module à 100% inférieur à 2,76 MPa (400 psi), un module à 300% inférieur à 4,83 MPa (700 psi) et un module à 500% inférieur à 10,34 MPa (1500 psi) à 22,2°C (72°F).

17. Polyuréthane selon la revendication 1, dans lequel le polyuréthane est préparé en l'absence d'un solvant.

18. Polyuréthane en phase aqueuse selon la revendication 1, dans lequel le composant de polyisocyanate est choisi dans le groupe constitué du diisocyanate d'isophorone, du 1,6-diisocyanate d'hexaméthylène, du diisocyanate de 1,12-dodécane, du diisocyanate de 2,2,4-triméthylhexaméthylène, du diisocyanate de 2,4,4-triméthylhexaméthylène, du diisocyanate de 2-méthyl-1,5-pentaméthylène, d'un mélange d'isomères 2,2,4 et 2,4,4 de diisocyanate de triméthylhexaméthylène et de leurs mélanges; le matériau à longue chaîne contenant de l'hydrogène actif est un polyester polyol qui a un poids moléculaire moyen de 2900 à 5500 daltons et qui est un liquide à 32,2°C (90°F) ou moins; et le rapport de NCO à OH est de 1,8/1 à 2,3/1.

19. Dispersion de polyuréthane en phase aqueuse comprenant le polyuréthane en phase aqueuse tel que défini selon l'une quelconque des revendications 1 à 18.

20. Film coulé à partir de la dispersion de polyuréthane en phase aqueuse définie selon la revendication 19, ledit film ayant des propriétés élastiques (mesurées selon la norme ASTM D 2370-82) comparables à celles du caoutchouc, une résistance à la traction supérieure à 24,19 MPa (3500 psi), un module à 100% inférieur à 3,10 MPa (450 psi), un module à 500% inférieur à 10,34 MPa (1500 psi) et un pourcentage d'allongement supérieur à 700% à 22,2°C (72°F).

21. Film selon la revendication 20, dans lequel le film est préparé en l'absence d'un solvant.

22. Gants médicaux comprenant le film selon la revendication 20.

23. Contraceptifs comprenant le film selon la revendication 20.

24. Cathéter comprenant le film selon la revendication 20.

Patentansprüche

1. Wässriges Polyurethan, wobei das Polyurethan das Reaktionsprodukt umfasst von:

(a) einer Polyisocyanat-Komponente, die aus der Gruppe ausgewählt ist, die aus einem aliphatischen Polyisocyanat, einem aromatischen Polyisocyanat, einem cycloaliphatischen Polyisocyanat und einem araliphatischen Polyisocyanat besteht;

(b) einem langkettigen, aktiven Wasserstoff enthaltenden Material, das 2 oder mehr aktive Wasserstoffatome pro Molekül enthält und aus der Gruppe ausgewählt ist, die aus einem Polyamid, einem Polyesterpolyol, einem Polycarbonatpolyol, einem Polyetherpolyol und Gemischen davon sowie einem aminterminierten Polypropylen glycol besteht; und

(c) einer wasserlöslich machenden Verbindung, die wasserlöslich machende Gruppen aufweist, welche aus der Gruppe ausgewählt sind, die aus Dimethylolpropansäure, Weinsäure, Dimethylolbutansäure, Glycolsäure, Thioglycolsäure, Milchsäure, Äpfelsäure, Dihydroxyäpfelsäure, Dihydroxyweinsäure und 2,6-Dihydroxybenzoesäure besteht, und in einer Menge im Bereich von 2 Gew.-% bis 4 Gew.-% des Gesamtprepolymers vorhanden ist;

unter Bildung eines Isocyanat-Prepolymers mit einem NCO:OH-Verhältnis von 1,3/1 bis 4,0/1, das durch Reaktion mit einem tertiären Amin neutralisiert, in Wasser dispergiert und durch Reaktion mit einem Amin kettenverlängert wird, wobei das Polyurethan in Filmform elastische Eigenschaften (gemessen gemäß ASTM D 2370-82), die mit Kautschuk vergleichbar sind, eine Zugfestigkeit von mehr als 24,19 MPa (3500 psi), einen 100%-Modul von unter 3,10 MPa (450 psi), einen 500%-Modul von unter 10,34 MPa (1500 psi) und eine prozentuale Dehnung von mehr als 700% bei 22,2 °C (72 °F) hat.

2. Polyurethan gemäß Anspruch 1, wobei das Polyisocyanat ein Diisocyanat ist.
3. Polyurethan gemäß Anspruch 1, wobei das NCO:OH-Verhältnis des Prepolymers 1,4/1 bis 3,0/1 beträgt.
4. Polyurethan gemäß Anspruch 1, wobei das NCO:OH-Verhältnis des Prepolymers 1,8/1 bis 2,3/1 beträgt.
5. Polyurethan gemäß Anspruch 1, wobei das NCO:OH-Verhältnis des Prepolymers 1,9/1 bis 2,1/1 beträgt.
6. Polyurethan gemäß Anspruch 2, wobei das Diisocyanat aus der Gruppe ausgewählt ist, die aus Isophorondiisocyanat, 2,2,4-Trimethylhexamethylenendiisocyanat, 2,4,4-Trimethylhexamethylenendiisocyanat und Gemischen davon besteht.
7. Polyurethan gemäß Anspruch 2, wobei das Diisocyanat aus der Gruppe ausgewählt ist, die aus Tetramethylxylol-diisocyanat (TMXDI), Cyclohexylbismethylenisocyanat (H₁₂MDI), Methanbis(4-phenylisocyanat) (MDI), Toluoldiisocyanat (TDI), 2,2,4- und 2,4,4-Isomergemisch von Trimethylhexamethylenendiisocyanat (TMDI) und Gemischen davon besteht.
8. Polyurethan gemäß Anspruch 1, wobei das Polyesterpolyol aus der Gruppe ausgewählt ist, die aus einem Hexandiolneopentylglycoladipat, Ethylenglycol/Diethylenglycoladipat und Ethylenglycol/Butadioladipat sowie Gemischen davon besteht.
9. Polyurethan gemäß Anspruch 1, wobei das langkettige Polyesterpolyol ein mittleres Molekulargewicht von 2900 bis 5500 Dalton hat.
10. Polyurethan gemäß Anspruch 1, wobei das Polyetherpolyol aus der Gruppe ausgewählt ist, die aus Polyethylenoxid, Polypropylenoxid und Gemischen davon besteht.
11. Polyurethan gemäß Anspruch 1, wobei das langkettige Amid ein aminterminiertes Polypropylenglycol ist.
12. Polyurethan gemäß Anspruch 1, wobei es sich bei der wasserlöslich machenden Verbindung um Dimethylolpropansäure handelt.
13. Polyurethan gemäß Anspruch 1, wobei das Amin für die Kettenverlängerung aus der Gruppe ausgewählt ist, die aus primären Aminen, sekundären Aminen, anorganischen Aminen und Gemischen davon besteht.
14. Polyurethan gemäß Anspruch 1, wobei das Amin für die Kettenverlängerung aus der Gruppe ausgewählt ist, die aus Diethylentriamin, Ethylendiamin, meta-Xylylendiamin, Aminoethylethanolamin, Hydrazin und Gemischen davon besteht.
15. Polyurethan gemäß Anspruch 1, wobei das tertiäre Amin aus der Gruppe ausgewählt ist, die aus Triethylamin, Dimethylethanolamin und N-Methylmorpholin besteht.
16. Polyurethan gemäß Anspruch 1, wobei der Film weiterhin einen 100%-Modul von unter 2,76 MPa (400 psi), einen 300%-Modul von unter 4,83 MPa (700 psi) und einen 500%-Modul von unter 10,34 MPa (1500 psi) bei 22,2 °C (72 °F) umfasst.

17. Polyurethan gemäß Anspruch 1, wobei das Polyurethan in Abwesenheit eines Lösungsmittels hergestellt wird.

18. Wässriges Polyurethan gemäß Anspruch 1, wobei die PolyisocyanatKomponente aus der Gruppe ausgewählt ist, die aus Isophorondiisocyanat, Hexamethylen-1,6-diisocyanat, 1,12-Dodecandiisocyanat, 2,2,4-Trimethylhexamethylendiisocyanat, 2,4,4-Trimethylhexamethylendiisocyanat, 2-Methyl-1,5-pentamethylendiisocyanat, 2,2,4- und 2,4,4-Isomergemisch von Trimethylhexamethylendiisocyanat und Gemischen davon besteht;

das langkettige, aktiven Wasserstoff enthaltende Material ein Polyesterpolyol mit einem mittleren Molekulargewicht von 2900 bis 5500 Dalton ist und bei 32,2 °C (90 °F) oder darunter eine Flüssigkeit ist; und

das NCO:OH-Verhältnis 1,8/1 bis 2,3/1 beträgt.

19. Wässrige Polyurethandispersion, die das wässrige Polyurethan gemäß einem der Ansprüche 1 bis 18 umfasst.

20. Film, der aus der wässrigen Polyurethandispersion gemäß Anspruch 19 gegossen ist, wobei der Film elastische Eigenschaften (gemessen gemäß ASTM D 2370-82), die mit Kautschuk vergleichbar sind, eine Zugfestigkeit von mehr als 24,19 MPa (3500 psi), einen 100%-Modul von unter 3,10 MPa (450 psi), einen 500%-Modul von unter 10,34 MPa (1500 psi) und eine prozentuale Dehnung von mehr als 700% bei 22,2 °C (72 °F) hat.

21. Film gemäß Anspruch 20, wobei der Film in Abwesenheit eines Lösungsmittels hergestellt wird.

22. Medizinische Handschuhe, die den Film gemäß Anspruch 20 umfassen.

23. Empfängnisverhütende Vorrichtungen, die den Film gemäß Anspruch 20 umfassen.

24. Katheter, die den Film gemäß Anspruch 20 umfassen.

